



Aluminum AlSi10Mg

DIRECT METAL LASER SINTERING MATERIAL SPECIFICATIONS

Highlights

- Low weight
- Good thermal properties, strength and hardness
- Fast building
- Excellent machinability

Applications

- Thin walls
- Complex geometries
- Lower cost prototypes
- Aerospace and automotive

TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	ENGLISH	METRIC	ENGLISH	METRIC
	STRESS RELIEVED - 35 C PLATFORM		HIP + T6 HEAT TREAT	
Ultimate Tensile Strength	55 ksi	379 MPa	41 ksi	281 MPa
0.2% Yield Strength	34 ksi	232 MPa	32 ksi	221 MPa
Elongation	6.9%	6.9%	14.1%	14.1%
Reduction of Area	10.2%	10.2%	20.7%	20.7%
Modulus of Elasticity	9.91 msi	68.3 GPa	10.29 msi	71.0 GPa
Hardness, Rockwell B	64	64	-	-

ALUMINUM ALSI10MG COMPOSITION

ELEMENT	TYPICAL PERCENTAGES
Aluminum (Al)	balance
Copper (Cu)	≤ 0.05
Iron (Fe)	≤ 0.55
Magnesium (Mg)	0.2 - 0.45
Manganese (Mn)	≤ 0.45
Silicon (Si)	9.0 - 11.0
Titanium (Ti)	≤ 0.15
Zinc (Zn)	≤ 0.10

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice. *Chemical analysis for specific lots available upon request.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.